



Nano-engineered Materials for Vehicle-to-grid Applications in Renewable Energy-integrated Smart Grids: A Critical Environmental Review

T. Ramesh¹, A. Soundararajan², K. Balachander^{2*}, M. Venkatesan³, A. Nagamani Prabu⁴, G. Jayanthi⁵ and Channu Lal⁶

¹Department of Electrical and Electronics Engineering, Karpagam Academy of Higher Education, Coimbatore, TN, India

²Department of Electrical and Electronics Engineering, Sri Ramakrishna Engineering College, Coimbatore, TN, India

³Department of Electronics and Communication Engineering, Dhanalakshmi Srinivasan College of Engineering, Coimbatore, TN, India

⁴Department of Physics, Karpagam Academy of Higher Education, Coimbatore, TN, India

⁵Department of Electrical and Electronics Engineering, Mahendra Engineering College, Namakkal, TN, India

⁶Department of Electrical and Electronics Engineering, Bishop Jerome Institute, Kollam, India

Received: 12.02.2026 Accepted: 24.03.2026 Published: 30.06.2026

*kaybe.ind@gmail.com



ABSTRACT

The convergence of electric mobility and renewable energy integration has intensified interest in vehicle-to-grid (V2G) systems as distributed energy storage solutions for smart grids. While V2G enhances renewable energy utilization and grid flexibility, frequent bidirectional cycling accelerates battery degradation and poses environmental sustainability challenges. Environmental nanotechnology offers transformative, material-level interventions through nano-engineered electrode architectures, solid-state nanocomposite electrolytes, nano-enhanced wide-bandgap power devices, and nanosensor-driven health diagnostics. This review critically evaluates the role of nanomaterials in improving electrochemical durability, thermal stability, conversion efficiency, and life cycle environmental performance in V2G-enabled systems. A comparative analysis of nano-engineered battery materials, nano-enhanced converters, and diagnostic technologies is presented. Environmental indicators, including life cycle emissions, resource conservation, and renewable energy integration efficiency, are systematically discussed. Key research gaps, scalability constraints, and commercialization challenges are identified to guide future interdisciplinary research at the intersection of environmental nanotechnology and smart grid engineering.

Keywords: Environmental nanotechnology; Vehicle-to-grid; Nanostructured electrodes; Renewable energy integration; Smart grid sustainability; Lithium-ion durability.

1. INTRODUCTION

The transition towards low-carbon energy infrastructures has accelerated the deployment of renewable energy sources across global power systems. Solar and wind generation offer substantial reductions in greenhouse gas emissions; however, their intermittency creates significant grid stability challenges. Energy storage has therefore become central to renewable integration strategies (Kempton *et al.* 2005). Electric vehicles (EVs), when integrated through vehicle-to-grid (V2G) frameworks (Fig. 1), provide decentralized storage capacity capable of frequency regulation, demand response, and peak load mitigation (Lund and Kempton, 2008). Despite these advantages, repeated bidirectional cycling induces material-level degradation mechanisms within lithium-ion batteries, including solid-electrolyte interphase thickening, lithium plating, structural phase transformation, and thermal instability (Saber and Venayagamoorthy, 2011). While prior literature has extensively explored communication protocols, economic incentives, and grid optimization algorithms, comparatively limited attention has been

directed toward material-scale innovations that determine the long-term sustainability of V2G systems. Environmental nanotechnology introduces advanced material architectures capable of enhancing electrochemical performance and reducing lifecycle environmental impact (Yilmaz and Krein, 2013).




Fig. 1: Integrated nano-enabled V2G framework for renewable smart grids

This review aims to critically synthesize current knowledge and identify pathways through which nano-engineered materials strengthen renewable-integrated smart grid systems (Kadir and Fung, 2025).

2. V2G SYSTEMS AND MATERIAL-LEVEL CHALLENGES

V2G operation fundamentally alters the electrochemical duty cycle of electric vehicle (EV) batteries when compared with conventional transportation use (Dubey and Santoso, 2015). In traditional EV applications, battery discharge is largely dictated by driving patterns, with relatively predictable charge–discharge intervals and controlled charging events. In contrast, V2G-enabled systems transform EV batteries into distributed grid assets that actively participate in frequency regulation, peak shaving, voltage stabilization, and renewable energy balancing (Hannan *et al.* 2017). This expanded operational role imposes significantly different electrochemical stresses at the material level. Unlike standard mobility-driven cycling, V2G participation is characterized by high-frequency partial state-of-charge (SoC) fluctuations. Grid-support applications often require rapid power injection and absorption in response to real-time grid conditions (Yohannes *et al.* 2025). As a result, batteries undergo numerous shallow micro-cycles within narrow SoC windows. Although shallow cycling is sometimes considered less damaging than deep cycling, repetitive micro-cycling at high frequency can accelerate interfacial degradation mechanisms, particularly the growth of the solid electrolyte interphase (SEI) layer on the anode surface (Yu *et al.* 2022).

Rapid charge–discharge transitions further intensify degradation. During high C-rate charging or discharging events, lithium-ion diffusion gradients become non-uniform, leading to localized lithium plating on graphite anodes. Lithium plating not only reduces reversible capacity but also poses safety risks due to dendrite formation. At the cathode side, high-rate operation induces mechanical stress caused by lattice expansion and contraction, which may initiate micro-cracks and particle fragmentation (Li *et al.* 2024). Over prolonged V2G participation, these microstructural instabilities accumulate, contributing to irreversible capacity loss. Thermal cycling represents another critical stress factor. V2G services frequently occur during peak demand periods or renewable intermittency events, which may coincide with elevated ambient temperatures (Leippi *et al.* 2024). Temperature fluctuations alter reaction kinetics and accelerate electrolyte decomposition. Elevated temperatures enhance parasitic side reactions, while low-temperature operation increases internal resistance and promotes lithium plating (Etacheri *et al.* 2011). The combination of electrical and thermal stress creates complex degradation pathways that

are not typically observed under conventional EV operation.

Extended dwell periods at intermediate state-of-charge levels also influence material stability. V2G scheduling strategies often maintain batteries within mid-range SoC bands (e.g., 40–80%) to ensure rapid availability for grid services. While this approach avoids deep-discharge extremes, prolonged residence at specific voltage plateaus can enhance transition-metal dissolution in layered-oxide cathodes, such as nickel–manganese–cobalt oxides (NMC). Dissolved metal ions may migrate to the anode surface, destabilizing the SEI and increasing impedance growth (Nitta *et al.* 2015).

These operational conditions collectively accelerate several well-documented degradation phenomena:

- Capacity fade, driven by loss of active lithium inventory and structural instability in electrode materials.
- Internal resistance growth, caused by SEI thickening and electrode–electrolyte interfacial deterioration.
- Electrolyte decomposition, intensified by thermal and electrochemical stress.
- Cathode structural degradation, including phase transitions and micro-cracking.

From an environmental perspective, accelerated degradation has broader implications. Reduced battery lifespan increases material extraction demands for lithium, nickel, cobalt, and manganese, thereby amplifying lifecycle environmental impacts. Frequent battery replacement also raises waste management challenges and embodied energy consumption associated with manufacturing. Therefore, sustainable V2G deployment cannot rely solely on grid-level optimization algorithms, pricing mechanisms, or communication protocols (Armand and Tarascon, 2008). While intelligent energy management can reduce extreme cycling, long-term viability fundamentally depends on improving material resilience at the nanoscale. Enhancing electrode stability, optimizing electrolyte formulations, and improving thermal tolerance through nano-engineered architectures are essential strategies for mitigating degradation under V2G conditions. In this context, environmental nanotechnology emerges as a critical enabler. By tailoring material morphology, surface chemistry, and structural integrity at the nanoscale, it becomes possible to enhance durability while simultaneously reducing lifecycle environmental burden. The integration of nano-engineered materials into V2G systems, therefore, represents not merely a performance enhancement strategy but a sustainability

imperative for renewable-integrated smart grids (Goodenough and Kim, 2010).

3. NANO-ENGINEERED ELECTRODE MATERIALS

3.1 Nanoscale Structural Optimization

Nanoscale structural engineering of electrode materials has emerged as a powerful strategy to enhance electrochemical performance, particularly under the demanding operational profiles associated with V2G systems. By reducing particle dimensions from the micrometre to nanometre scale, fundamental transport and interfacial processes within lithium-ion batteries can be significantly modified. These modifications influence ion diffusion, electronic conductivity, mechanical stability, and thermal response (Manthiram *et al.* 2020).

One of the primary advantages of reducing electrode particle size lies in the shortening of lithium-ion diffusion pathways. In bulk electrode materials, lithium ions must travel relatively long distances through solid lattices during insertion and extraction processes. Under high-rate V2G cycling conditions, such diffusion limitations contribute to polarization losses and incomplete utilization of active material. Nanostructured cathodes, by contrast, exhibit substantially reduced diffusion lengths, enabling faster ion transport and improved reaction kinetics. This structural refinement enhances rate capability and allows batteries to respond rapidly to grid-support demands without severe voltage drops (Zhang *et al.* 2006).




Fig. 2: Schematic illustration of degradation mechanisms in conventional and nanostructured electrodes

In addition to improved ion transport, nanoscale materials increase the effective electrode–electrolyte interfacial area. A larger surface-to-volume ratio promotes enhanced electrochemical reactivity and facilitates more uniform current distribution across active particles. Uniform current distribution reduces localized overpotentials and mitigates the formation of hot spots

during rapid charge–discharge transitions. For V2G applications, where frequent shallow cycling is common, this improved interfacial homogeneity contributes to more stable dynamic performance. Nano-structuring also influences mechanical behaviour. Many cathode materials, particularly layered transition-metal oxides (e.g., NMC and nickel–cobalt–aluminum oxides [NCA]), undergo anisotropic lattice expansion and contraction during lithium intercalation. In larger particles, repeated volumetric strain may induce microcrack formation and particle fragmentation. Nanostructured architectures better accommodate strain due to their smaller domain size, reducing mechanical stress accumulation and enhancing structural integrity under cyclic loading. This mechanical resilience is particularly valuable under bidirectional V2G operation, which imposes repetitive micro-cycling stress (Millán *et al.* 2014).

Despite these advantages, nanoscale structural optimization introduces new challenges. The increased surface area, while beneficial for kinetics, also elevates surface reactivity. High surface energy promotes intensified side reactions between electrode surfaces and electrolyte components. These parasitic reactions accelerate SEI growth on the anode and trigger surface reconstruction phenomena on cathode materials. Excessive SEI formation consumes active lithium inventory and increases internal resistance, thereby contributing to capacity fade. Furthermore, surface instability in high-nickel cathodes can lead to transition metal dissolution and surface phase transformation from layered to spinel or rock-salt structures. These transformations degrade electrochemical reversibility and compromise long-term durability (Fig. 2). Under V2G conditions involving repeated partial cycling, such surface-driven degradation mechanisms can be amplified (Ali and Lee, 2021).

To counteract these limitations, surface modification strategies are essential. Conformal nanocoatings, such as metal oxides (Al_2O_3 , TiO_2), phosphates, or carbon layers, can serve as protective barriers that suppress electrolyte decomposition while maintaining ionic conductivity. Atomic layer deposition (ALD) techniques enable precise coating thickness control at the nanoscale, ensuring minimal impedance penalty. Similarly, core–shell and composite electrode architectures provide mechanical buffering and chemical stabilization. Composite integration strategies also play a critical role. For example, silicon–carbon nanocomposites incorporate conductive carbon matrices to mitigate silicon’s volumetric expansion during lithiation. This design enhances structural stability while preserving high specific capacity. In cathode systems, embedding nanoparticles within conductive networks improves electron transport and reduces polarization under high-rate operations (Baumgartner *et al.* 2025).

Table 1. Comparison of bulk and nanostructured electrode materials under V2G operating conditions

Parameter	Bulk Electrode Materials	Nano-Structured Electrode Materials	Implication for V2G Applications
Particle Size	Micrometer-scale particles	Nanometer-scale particles (1–100 nm)	Reduced diffusion limitations in nanostructured systems
Lithium-Ion Diffusion Path Length	Long diffusion pathways	Significantly shortened diffusion pathways	Faster response to rapid grid support events
Electrode–Electrolyte Interface Area	Limited surface contact	High surface-to-volume ratio	Improved reaction kinetics but increased surface reactivity
Rate Capability	Moderate; performance drops at high C-rate	Enhanced high-rate performance	Better suitability for frequent V2G micro-cycling
Polarization Loss	Higher polarization under dynamic load	Reduced polarization due to improved kinetics	Improved voltage stability during bidirectional operation
Mechanical Stress Tolerance	Higher risk of particle cracking under cycling	Better strain accommodation due to smaller particle domains	Enhanced durability under repetitive partial cycling
Thermal Stability	Moderate; localized heat accumulation possible	Improved heat dissipation due to distributed reaction sites	Reduced thermal gradients in grid-interactive operation
Surface Reactivity	Lower surface energy	Elevated surface reactivity	Requires surface coatings to suppress parasitic reactions
SEI Formation	Slower but thicker over time	Faster formation due to a larger surface area	Needs interface engineering for long-term stability
Electrolyte Decomposition Risk	Moderate	Increased risk without a protective coating	Necessitates nanocoating strategies
Manufacturing Complexity	Established large-scale fabrication	More complex synthesis methods	Scalability remains a challenge
Lifecycle Environmental Impact	Shorter lifespan → more replacements	Extended cycle life potential	Reduced material extraction and waste generation (if stabilized)
Suitability for V2G Duty Cycles	Limited durability under high-frequency cycling	More adaptable to rapid, shallow charge–discharge cycles	Preferred for sustainable V2G deployment

From an environmental nanotechnology perspective, nanoscale optimization must balance performance enhancement with sustainability considerations. Although nano-engineered materials improve cycle life and energy efficiency, their synthesis often involves energy-intensive processes or rare materials. Therefore, scalable and environmentally

responsible fabrication methods are necessary to ensure that performance gains translate into net environmental benefits. In summary, nanoscale structural optimization enhances ion transport kinetics, reduces polarization, improves rate capability, and increases mechanical resilience, which are key requirements for V2G-enabled battery systems. However, increased surface reactivity and parasitic degradation necessitate protective coatings and composite engineering strategies. Sustainable implementation of nanostructured electrodes thus requires an integrated approach that simultaneously addresses electrochemical durability, manufacturing scalability, and lifecycle environmental impact.

Table 1 compares bulk and nanostructured electrode materials under V2G operating conditions, highlighting the differences in ion transport, mechanical stability, and degradation behaviour. The analysis demonstrates the superior suitability of nano-engineered electrodes for high-frequency, bidirectional V2G cycling when appropriate surface stabilization strategies are employed.

3.2 Comparative Analysis of Nano-engineered Cathode Materials

Table 2 presents a comparative assessment of major nano-engineered cathode architectures relevant to V2G deployment. Each material system exhibits distinct electrochemical, environmental, and technological trade-offs that influence its suitability for renewable-integrated smart grids.

Table 2. Comparison of nano-engineered cathode architectures for V2G applications

Material System	Key Advantage	Limitation	Environmental Impact	Technology Readiness
Nano-LFP	Thermal stability	Moderate energy density	Lower fire risk	High
Nano-NMC	High energy density	Cobalt dependency	Resource intensity	High
Silicon–Carbon Composite	High capacity	Volume expansion	Extended cycle life potential	Medium
Solid-state Nano Composite	Enhanced safety	Manufacturing complexity	Reduced leakage	Low–Medium

Nanostructured Lithium Iron Phosphate (nano-LFP) is widely recognized for its excellent thermal stability and structural robustness. The olivine crystal structure of LFP resists oxygen release at elevated temperatures, significantly reducing thermal runaway risks. When engineered at the nanoscale, LFP demonstrates enhanced lithium-ion diffusion kinetics and improved rate capability, making it suitable for high-frequency V2G micro-cycling. However, its moderate energy density limits driving range compared to layered oxide chemistries. From an environmental perspective, nano-LFP is advantageous due to the absence of cobalt and the relatively lower toxicity of iron and phosphate components. Its high technology readiness level and

established manufacturing infrastructure make it a strong candidate for near-term sustainable V2G integration.

Nanostructured NMC offers superior energy density and high power capability, which are attractive for grid-support applications requiring rapid energy exchange. Nanoscale optimization improves structural stability and rate performance under dynamic cycling conditions. Nevertheless, cobalt dependency introduces significant environmental and ethical concerns related to mining practices and resource scarcity. Additionally, high nickel content in advanced NMC variants may increase structural instability under prolonged V2G cycling. Although nano-NMC systems are technologically mature and commercially deployed, their long-term sustainability depends on reducing cobalt content and improving recycling efficiency.

Silicon-carbon nanocomposites, primarily utilized in anode architectures, are included due to their relevance in high-capacity V2G battery systems. Silicon offers exceptionally high theoretical capacity; however, it undergoes significant volumetric expansion during lithiation, often exceeding 300%. Nanoscale engineering and carbon matrix integration mitigate mechanical fracture by buffering expansion stress. In V2G applications, where repeated partial cycling occurs, silicon-carbon composites can extend cycle life if mechanical degradation is effectively controlled. Environmentally, improved capacity may reduce battery mass and material usage per unit energy, yet scalable manufacturing and long-term durability remain challenges. Current technology readiness is moderate, with ongoing industrial adoption.

Solid-state nanocomposites represent an emerging architecture aimed at improving safety and eliminating flammable liquid electrolytes. Nano-engineered solid electrolytes enhance ionic conductivity while maintaining mechanical strength. For V2G systems, solid-state batteries offer potential advantages in thermal stability and reduced leakage risks, which are critical for distributed grid assets operating under varying environmental conditions. However, manufacturing complexity, interfacial resistance, and scalability constraints limit current commercialization. Environmental benefits may arise from enhanced safety and longer service life, but lifecycle impacts depend heavily on fabrication processes and material sourcing.

Although nano-structuring consistently improves electrochemical durability, rate capability, and mechanical resilience under V2G stress profiles, these enhancements must be evaluated within a broader sustainability framework. Scalability of nano-synthesis techniques, energy intensity of production processes, and critical raw material dependency remain significant environmental constraints.

- High-nickel chemistries may reduce cobalt content but increase processing complexity.
- Advanced nanocoating techniques, such as ALD, enhance stability but may increase manufacturing energy demand.
- Solid-state systems promise safety improvements but require rare materials and high-temperature processing.

Therefore, while nano-engineered cathode architectures demonstrate strong technical suitability for V2G-enabled renewable integration, long-term sustainability depends on integrating material innovation with responsible sourcing, efficient recycling pathways, and scalable green manufacturing practices. In conclusion, nano-LFP currently presents the most environmentally balanced near-term solution; nano-NMC offers high-performance advantages but raises resource concerns; silicon-carbon composites provide capacity expansion potential with further optimization; and solid-state nanocomposites represent a promising but technologically evolving pathway.

4. NANO-ENHANCED POWER ELECTRONIC INTERFACES

In V2G systems, bidirectional power converters serve as the critical interface between electric vehicles and the smart grid. These converters regulate energy flow during both charging and grid-support discharging operations. Their efficiency, thermal stability, and switching performance directly influence overall system reliability, battery stress, and environmental sustainability. Conventional silicon-based (Si) power semiconductor devices have dominated power electronics for decades. However, their intrinsic material limitations, including relatively narrow bandgap energy, lower breakdown voltage, and higher switching losses, restrict performance under high-frequency and high-temperature operation. V2G applications, characterized by frequent bidirectional switching and dynamic load variations, demand superior converter efficiency and thermal tolerance.




Fig. 3: Efficiency comparison of conventional and wide-bandgap nano-enhanced converters

Wide-bandgap (WBG) semiconductor materials, particularly silicon carbide (SiC) and gallium nitride (GaN), represent a transformative advancement enabled by nanoscale material engineering. Their larger bandgap energy permits operations at higher voltages, higher temperatures, and higher switching frequencies compared to conventional silicon devices. Fig. 3 illustrates the efficiency variation of conventional silicon and wide-bandgap (SiC/GaN) converters across different load conditions. SiC/GaN devices consistently demonstrate higher efficiency and reduced performance degradation at higher loads, highlighting their suitability for V2G applications requiring dynamic bidirectional power flow.

Reduced Switching Losses: Nano-engineered SiC/GaN devices exhibit significantly lower switching energy dissipation due to reduced parasitic capacitance and faster charge carrier mobility. This reduction improves conversion efficiency during rapid bidirectional transitions common in V2G services such as frequency regulation.

Higher Operating Temperatures: WBG devices can operate at elevated junction temperatures without substantial performance degradation. This capability reduces dependency on bulky cooling systems and improves compactness, which is an important consideration for onboard EV integration.

Improved Overall Efficiency: Enhanced switching characteristics enable converter efficiencies exceeding 94–97%, compared to 88–92% typical of silicon-based systems. Higher efficiency reduces energy loss as heat, lowers grid-side energy waste, and minimizes indirect carbon emissions associated with generation losses.

Table 3. Performance comparison of conventional and nano-enhanced converters

Parameter	Conventional Si-Based	SiC/GaN-based (Nano-enhanced)
Efficiency	88–92%	94–97%
Thermal Loss	High	Reduced
Cooling Requirement	Significant	Lower
Lifespan	Moderate	Extended

Table 3 compares conventional silicon converters with SiC/GaN nano-enhanced alternatives across key performance parameters. The higher efficiency range of WBG devices translates into measurable environmental benefits. Even a 3–5% improvement in conversion efficiency can significantly reduce cumulative energy losses over the operational lifetime of a V2G-enabled vehicle fleet. Reduced thermal losses also lower cooling system requirements,

decreasing auxiliary energy consumption and material use. An extended lifespan arises from improved thermal stability and reduced mechanical stress due to lower heat cycling. This durability reduces component replacement frequency, contributing to material conservation and improved lifecycle sustainability. However, cost barriers remain a substantial constraint. WBG semiconductor fabrication requires advanced material processing techniques, and wafer production yields are still evolving. Additionally, supply chain concentration and raw material sourcing challenges may limit rapid global scalability. Therefore, while nano-enhanced converters offer clear technical and environmental advantages, widespread adoption depends on continued manufacturing optimization and cost reduction.

5. NANOSENSOR INTEGRATION AND HEALTH MONITORING

Battery health management plays a decisive role in ensuring sustainable V2G deployment. Conventional battery management systems (BMS) rely on voltage, current, and temperature measurements at relatively coarse resolution. In contrast, nanoscale sensing technologies introduce high-precision, distributed diagnostics capable of detecting early-stage degradation phenomena. Nanosensors embedded within battery modules or integrated along current collectors can provide:

- High-resolution state-of-charge (SoC) estimation through enhanced electrochemical impedance tracking.
- Real-time state-of-health (SoH) assessment by monitoring microstructural or impedance variations.
- Detailed thermal gradient mapping, enabling localized overheating detection.
- Mechanical strain measurement for early crack formation identification in electrode materials.

Such granular monitoring is particularly valuable under V2G duty cycles, where frequent partial cycling accelerates subtle degradation mechanisms. When combined with predictive analytics and machine learning algorithms, nanosensor data enable degradation-aware scheduling. For example, grid services can be dynamically allocated to vehicles exhibiting higher health margins, thereby distributing stress more evenly across a fleet. This intelligent dispatch strategy extends aggregate battery life and reduces premature replacement.

Despite these advantages, nanosensor deployment introduces several technical and operational challenges:

- **Sensor Drift:** Long-term exposure to electrochemical environments may alter calibration accuracy.
- **Data Security Risks:** Increased data transmission between vehicles and grid infrastructure creates cybersecurity vulnerabilities.
- **Reliability Concerns:** Embedded sensors must withstand vibrations, temperature variations, and chemical exposure over extended operational lifetimes.

Addressing these limitations requires robust encapsulation strategies, secure communication architectures, and redundancy-based fault detection systems.

6. ENVIRONMENTAL LIFECYCLE ANALYSIS

The integration of nano-engineered materials into V2G systems must be evaluated through a lifecycle sustainability framework rather than isolated performance metrics. Lifecycle assessment (LCA) considers raw material extraction, manufacturing energy demand, operational efficiency, and end-of-life disposal or recycling. Improved durability directly reduces the need for:

- Frequent battery replacement
- Intensive mining of lithium, nickel, and cobalt
- Energy-intensive manufacturing cycles
- Disposal-related environmental burdens

Table 4. Environmental impact indicators

Indicator	Baseline V2G	Nano-enhanced system
Battery Replacement	Standard	Reduced
Lifecycle CO ₂ Emission	Higher	Lower
Renewable Utilization	Moderate	Improved
Thermal Energy Waste	Higher	Reduced

Table 4 and Fig. 4 compare environmental performance indicators between baseline V2G systems and nano-enhanced alternatives. Reduced battery replacement frequency leads to significant cumulative reductions in embodied energy and greenhouse gas emissions. Lower thermal energy waste, due to improved converter efficiency and reduced internal resistance growth, decreases overall system carbon intensity. Enhanced renewable utilization arises from improved storage responsiveness and reliability, allowing higher penetration of intermittent energy sources without compromising grid stability.




Fig. 4: Lifecycle environmental impact reduction with nano-enhanced systems

Even moderate improvements in cycle life, such as a 15–20% extension, can produce substantial reductions in cumulative CO₂ emissions over a fleet's operational lifespan. However, these benefits must be weighed against the environmental cost of advanced nanomaterial fabrication processes. Sustainable synthesis routes and recycling-compatible material design are therefore essential.

7. ECONOMIC AND SCALABILITY CONSIDERATIONS

Although nanotechnology significantly enhances technical performance and environmental durability in V2G-enabled smart grids, its long-term economic viability is shaped by a complex interplay of interdependent factors. Manufacturing cost remains a primary concern, as advanced nano-fabrication techniques, such as atomic layer deposition, nanocoating processes, and precision doping, often require sophisticated equipment and high capital investment. While these techniques improve material stability and efficiency, reducing cost per unit through economies of scale, streamlined process integration, and energy-efficient production methods is essential for commercial competitiveness. In parallel, material sourcing introduces additional uncertainty. Many nano-enabled systems rely on critical minerals such as gallium, rare-earth elements, and cobalt, whose supply chains are geographically concentrated and susceptible to geopolitical fluctuations. This dependency can create price volatility and long-term resource security challenges, potentially offsetting environmental gains if not managed responsibly.

Beyond production considerations, market structure plays a decisive role in adoption. Effective V2G compensation frameworks must provide sufficient financial incentives to EV owners to justify battery participation in grid services, particularly given the perceived risk of accelerated degradation. Without

transparent and attractive revenue-sharing mechanisms, user participation may remain limited. Furthermore, policy frameworks directly influence the pace of commercialization. Regulatory support for renewable integration, smart grid modernization, recycling infrastructure, and critical material recovery is necessary to create a stable ecosystem for nano-enabled technologies. Ultimately, large-scale adoption requires synchronized advancement across nanomaterial production, power converter manufacturing, battery lifecycle management, and supportive energy policies. In the absence of coordinated planning, technological innovation alone cannot ensure sustainable and economically viable deployment of nano-enhanced V2G systems.

8. RESEARCH GAPS AND FUTURE DIRECTIONS

Despite notable advancements in nanomaterial engineering, power electronics, and smart grid integration, several critical research gaps must be addressed before nano-enabled V2G systems can achieve large-scale, sustainable deployment. One of the most pressing challenges is the lack of long-term field validation. Much of the existing performance data is derived from controlled laboratory-scale cycling experiments, which may not accurately replicate real-world V2G duty profiles. In practice, batteries are exposed to fluctuating temperatures, variable load conditions, irregular grid interactions, and diverse user behavior. Longitudinal field studies under realistic operational environments are therefore essential to validate degradation models and confirm durability projections. Another significant gap lies in the absence of standardized environmental performance metrics. Current lifecycle assessments often vary in system boundaries, assumptions, and impact categories, making cross-comparison between nano-enhanced and conventional systems difficult. Developing unified evaluation frameworks that incorporate material extraction, manufacturing energy intensity, operational efficiency, and end-of-life recovery is critical for transparent sustainability assessment.

Integrated techno-economic modelling also remains underdeveloped. While nanomaterial innovations demonstrate measurable improvements in electrochemical performance and converter efficiency, comprehensive models linking these improvements to grid economics, battery degradation rates, carbon reduction potential, and revenue generation are limited. Bridging material-level advancements with macro-level economic and environmental indicators is necessary to quantify real-world value and inform policy decisions. Recycling pathways for nano-enhanced components present an additional concern. Advanced nanocomposites, protective coatings, and hybrid material architectures may complicate existing battery recycling processes. Without early incorporation of design-for-

recyclability principles, next-generation materials could inadvertently increase end-of-life processing complexity. Research efforts must therefore prioritize circular economy integration, including efficient material recovery and environmentally responsible disposal strategies.




Fig. 5: Research gaps and future integration pathways

Future progress demands interdisciplinary collaboration across material science, environmental engineering, data analytics, power electronics, and smart grid system design. Only through coordinated innovation, spanning nanoscale material development to policy-level implementation, can nano-enabled V2G architectures achieve durable, economically viable, and environmentally sustainable integration within renewable-dominated energy systems (Fig. 5).

9. CONCLUSION

The integration of V2G systems within renewable-dominated smart grids represents a transformative pathway towards decentralized, low-carbon energy infrastructures. However, the long-term viability of V2G deployment depends not only on grid-level optimization and market mechanisms but also on the durability, efficiency, and environmental performance of underlying material systems. In this context, nanotechnology offers a material-centric approach capable of addressing fundamental electrochemical, thermal, and structural limitations associated with high-frequency bidirectional energy exchange.

Nano-engineered electrode architectures enhance lithium-ion diffusion kinetics, improve mechanical strain accommodation, and reduce polarization losses under dynamic cycling conditions. Surface-modified cathodes, silicon-carbon nanocomposites, and solid-state nano-electrolytes collectively contribute to extended cycle life and improved safety profiles. Simultaneously, nano-enabled wide-bandgap power electronic devices such as SiC/GaN converters significantly reduce switching losses and thermal dissipation, thereby increasing system-level efficiency.

The integration of nanoscale sensing platforms further enables high-resolution diagnostics and predictive health management, allowing degradation-aware grid participation strategies that distribute stress intelligently across vehicle fleets.

From an environmental perspective, these improvements translate into reduced battery replacement frequency, lower lifecycle greenhouse gas emissions, and enhanced renewable energy utilization. Even moderate extensions in cycle life can substantially decrease cumulative raw material extraction and manufacturing-related carbon intensity. Consequently, nanotechnology not only strengthens technical performance but also reinforces the sustainability foundation of renewable-integrated smart grids. Despite these advantages, several barriers must be systematically addressed before widespread commercialization.

Manufacturing scalability, cost-intensive nanofabrication processes, critical material dependency, and recycling complexities remain significant challenges. Additionally, comprehensive lifecycle assessments and standardized environmental metrics are required to ensure that performance gains at the nanoscale yield net environmental benefits at the system level. Future progress will require coordinated, interdisciplinary efforts bridging materials science, power electronics engineering, environmental lifecycle modeling, data analytics, and policy development.

The convergence of environmental nanotechnology and smart grid infrastructure thus represents a critical frontier for resilient energy systems capable of supporting large-scale renewable energy penetration. By integrating material innovation with sustainable manufacturing practices and supportive regulatory frameworks, nano-enabled V2G architectures can play a decisive role in accelerating the global transition toward secure, efficient, and low-carbon energy ecosystems.

FUNDING

This research received no specific grant from any funding agency in the public, commercial, or not-for-profit sectors.

CONFLICTS OF INTEREST

The authors declare that there is no conflict of interest.

COPYRIGHT

This article is an open-access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).



REFERENCES

- Ali, Y. and Lee, S., An integrated experimental and modeling study of the effect of solid electrolyte interphase formation and Cu dissolution on CuCo₂O₄-based Li-ion batteries, *Int. J. Energy Res.*, 46(3), 3017–3033(2021).
<https://doi.org/10.1002/er.7359>
- Armand, M. and Tarascon, J. M., Building better batteries, *Nat.*, 451(7179), 652–657 (2008).
<https://doi.org/10.1038/451652a>
- Baumgartner, N., Sloot, D., Günther, A. and Hahnel, U. J. J., Development and test of a dual pathway model of personal and community factors driving new energy technology adoption: Case of V2G in three European countries, *Ecol. Econ.*, 230, 108514 (2025).
<https://doi.org/10.1016/j.ecolecon.2024.108514>
- Dubey, A. and Santoso, S., Electric vehicle charging on residential distribution systems: Impacts and mitigations, *IEEE Access*, 3, 1871–1893 (2015).
<https://doi.org/10.1109/ACCESS.2015.2476996>
- Etacheri, V., Marom, R., Elazari, R., Salitra, G. and Aurbach, D., Challenges in lithium-ion batteries: A review, *Energy Environ. Sci.*, 4(9), 3243–3262 (2011).
<https://doi.org/10.1039/C1EE01598B>
- Goodenough, J. B. and Kim, Y., Challenges for rechargeable Li batteries, *Chem. Mater.*, 22, 587–603 (2010).
<https://doi.org/10.1021/cm901452z>
- Hannan, M. A., Hoque, M. M., Mohamed, A. and Ayob, A., Battery energy storage systems for electric vehicles: Issues and challenges, *Renew. Sustain. Energy Rev.*, 69, 771–789 (2017).
<https://doi.org/10.1016/j.rser.2016.11.171>
- Kadir, N. and Fung, A. S., Integrated Micro- and Nano-Grid with Focus on Net-Zero Renewable Energy—A Survey Paper, *Energies*, 18(4), 794(2025).
<https://doi.org/10.3390/en18040794>
- Kempton, W. and Tomić, J., Vehicle-to-grid power implementation: From stabilizing the grid to supporting large-scale renewable energy, *J. Power Sources*, 144, 280–294 (2005).
<https://doi.org/10.1016/j.jpowsour.2004.12.022>
- Leippi, A., Fleschutz, M., Davis, K., Klingler, A.-L. and Murphy, M. D., Optimizing electric vehicle fleet integration in industrial demand response, *Appl. Energy*, 374, 123995 (2024).
<https://doi.org/10.1016/j.apenergy.2024.123995>
- Li, S., Zhao, P., Gu, C., Bu, S., Li, J. and Cheng, S., Integrating incentive factors in the optimization for bidirectional charging of electric vehicles, *IEEE Trans. Power Syst.*, 39(2), 4105–4116 (2024).
<https://doi.org/10.1109/TPWRS.2023.3308233>
- Lund, H. and Kempton, W., Integration of renewable energy into the transport and electricity sectors through V2G, *Energy Policy*, 36(9), 3578–3587 (2008).
<https://doi.org/10.1016/j.enpol.2008.06.007>

- Manthiram, A., A reflection on lithium-ion battery cathode chemistry, *Nat. Commun.*, 11(1), 1550 (2020).
<https://doi.org/10.1038/s41467-020-15355-0>
- Millán, J., Godignon, P., Perpiñà, X., Pérez-Tomás, A. and Rebollo, J., A survey of wide bandgap power semiconductor devices, *IEEE Trans. Power Electron.*, 29(5), 2155–2163 (2014).
<https://doi.org/10.1109/TPEL.2013.2268900>
- Nitta, N., Wu, F., Lee, J. T. and Yushin, G., Li-ion battery materials: Present and future, *Mater. Today*, 18(5), 252–264 (2015).
<https://doi.org/10.1016/j.mattod.2014.10.040>
- Saber, A. Y. and Venayagamoorthy, G. K., Plug-in vehicles and renewable energy sources for cost and emission reductions, *IEEE Trans. Ind. Electron.*, 58(4), 1229–1238 (2011).
<https://doi.org/10.1109/TIE.2010.2047828>
- Yilmaz, M. and Krein, P. T., Review of benefits and challenges of vehicle-to-grid technology, *IEEE Energy Convers. Exposition*, 3082-3089 (2012).
<https://doi.org/10.1109/ECCE.2012.6342356>
- Yohannes, G. and Huaiyong, L., Nanoenabled bioinnovations and decentralized climate-adaptive systems for enhancing agroenergetic resilience: a review article, *Dis. Nano.*, 20, 203(2025).
<https://doi.org/10.1186/s11671-025-04382-9>
- Yu, H., Niu, S., Shang, Y., Shao, Z., Jia, Y. and Jian, L., Electric vehicles integration and vehicle-to-grid operation in active distribution grids, *Renew. Sustain. Energy Rev.*, 168, 112812 (2022).
<https://doi.org/10.1016/j.rser.2022.112812>
- Zhang, S. S., A review on electrolyte additives for lithium-ion batteries, *J. Power Sources*, 162(2), 1379–1394 (2006).
<https://doi.org/10.1016/j.jpowsour.2006.07.074>