



Alkannatinctoria Barks as Organic Photo Sensitizers for Dye Sensitized TiO₂ Thin Film Solar Cells

K. Rajendran¹, S. Karthikeyan², V. Vetrivel^{3,4*}

¹Department of Electronics, LRG Government Arts College for Women, Tirupur, TN, India

²Department of Chemistry, Chikkanna Govt. Arts College, Tirupur, TN, India

³Department of Electronics, Sri Vasavi College, Erode, TN, India

⁴Department of Electronics and Communication Systems, Sri Krishna Arts & Science College, Coimbatore, TN, India

Received: 12.07.2016

Accepted: 22.09.2016

Published: 30-09-2016

*2vetrivel@gmail.com



ABSTRACT



Nano structured TiO₂ thin film dye-sensitized solar cells have been fabricated using TiO₂ photoelectrode sensitized using the extracts of Alkannatinctoria barks as organic sensitizers and their characteristics have been studied. The organic extracts having Alkannin pigment, which have hydroxyl and carboxylic groups in the molecule can attach effectively to the surface of TiO₂ film. The UV-Vis absorbance spectra of organic extract found to be maximum of 692 nm. The solar cell constructed using the Alkannatinctoria barks sensitized TiO₂ photo-electrode exhibited a short-circuit photocurrent of 6.08 E-5 A and a power conversion efficiency of 0.0971%. Organic dye sensitized TiO₂ photo electrodes present the prospect to be used as an environment-friendly, low-cost alternative system.

Keywords: AlkannaTinctoria; Organic dye sensitized; Power conversion efficiency; TiO₂.

1. INTRODUCTION

Dye sensitized solar cells (DSSCs) have attracted considerable interest as a low cost photovoltaic technology for building integration and indoor application (Liska *et al.* 1988; O'Regan and Graetzel, 1991; Graetzel, 2005; Maldonado, 2007). Sensitization of wide band gap semiconductor electrodes with dyes absorbing visible light has been a topic of continuous interest since its theoretical and experimental foundation by Gerischer, Tributsch and Calvin in the early '70s (Gerischer, 1971; Keis, 1991). The limited light harvesting efficiency of a dye monolayer on a semiconductor monocrystal lead to the advent of porous films consisting of nanometer sized semiconductor nanoparticles TiO₂ (O'Regan and Graetzel, 1991), ZnO (Keis, 1999; Martinson *et al.* 2009), SnO₂ (Bauer *et al.* 2002; Chappel *et al.* 2002), Nb₂O₅ (Sayama *et al.* 1998) that allowed for a dramatic enhancement of the effective surface area, thus making light absorption efficient in a single dye monolayer adsorbed on each particle.

The basic events of semiconductor sensitization can be schematized as follows,



A schematic picture of the processes, which are at the basis of the functioning of sandwich type solar devices, is shown in fig.1.

In equation (1) the sensitizer (S), upon photon absorption, is promoted to an electronically excited state (S*). If this state lies energetically above the conduction band of the semiconductor, electron injection to the empty states of the semiconductor can occur on a very fast time scale, equation (2), successfully competing with the other excited state deactivation pathways (radiative and non radiative processes).

The oxidized sensitizer (S+) is then regenerated by a redox electrolyte (usually the I/I₃ couple) according to process equation (3), in order to prevent electron recapture as the following process,



The I/I₃ system, dissolved in organic solvents, has been almost universally used as a charge carrier in dye sensitized photo electrochemical cells, since oxidation of iodide by the photo oxidized dye is usually fast and effectively competes with equation (4). Recently much attention has also been devoted to the development of alternative redox couples based on non corrosive transition metal complexes (Sapp *et al.* 2002). Generally, synthetic organic dyes (Yum *et al.* 2007; Campbell *et al.* 2007; Tian *et al.* 2009) and transition metal coordination compounds [mostly ruthenium (Nazeeruddin *et al.* 1993;

Nazeeruddin *et al.* 2001) and osmium (Kuciauskas *et al.* 2001, Argazzi *et al.* 2004; Altobello *et al.* 2005) polypyridil complexes have been used as effective sensitizers, since they couple broad and intense charge transfer bands to favourable ground and excited state energetics for the electron transfer reactions in equation (2) and (3). However, the preparation routes for metal complexes are often based on multi step procedures involving tedious and expensive chromatographic purification procedures. Thus, for both practical and fundamental reasons, some groups have investigated the possibility of achieving solar energy conversion exploiting nanocrystalline TiO₂ sensitization with natural pigments. In nature, fruit, vegetable, leaves, flowers and algae contain several dyes which can be easily extracted and employed in dyesensitized solar cells. For example, Tennakone *et al.* (1997) investigated the use of tannins and related phenolic substances extracted from black tea, nuts and pomegranate, as well anthocyanins from flowers and leaves. Dai and Rabani, (2001; 2002), Sarto Polo and Murakami Iha, (2006; 1936), Zhang (2008), Calogero and Bignozzi (2008) investigated anthocyanins and betalain pigments extracted from a variety of vegetable species typical of mediterranean, tropical and subtropical areas. Kay and Graetzel (1993) were probably the first to elucidate the photo electrochemical behaviour of natural chlorophylls as well as anthocyanin dyes from California blackberry (Cherepy *et al.* 1997). In this work we report, extracts of *Alkannatinctoria* barks used as sensitizer for nanocrystalline TiO₂ thin film for DSSC construction and their structural and optical and IV characteristics were studied.




Fig. 1: Schematic representation of the working principle and assembly of a sandwich type cell

2. EXPERIMENTAL METHOD

The titania (TiO₂) nano powder was prepared using sol-gel and hydrothermal method. The precursor used for titania is Titanium tetra isopropoxide (TTIP) and the solvent was 2-propanol. The precursor TTIP of 7.7 mL is taken in a 250 mL beaker, later 105 mL of

2-propanol was added under stirring. The mixture was kept in stirring for one hour and later titanium tetra isopropoxide was added drop wise in continuous stirring until the solution mixture turns in to sol-gel homogenous state with moon stone yellow colour. The measured pH was 5.8 in sol-gel. Thus prepared sol-gel was transferred in to stirrer less stainless steel teflon coated autoclave and sealed with SS lid. The autoclave with sol-gel was aged in hot air oven at 120 °C for 24 hrs and later at elevated hydro thermal temperature of 150 °C for 48 hrs. The obtained white solids were centrifuged with deionised water at 4500 RPM for 15 min. The solid parts are dried in hot air oven for 12 hrs at 150 °C and motored to fine powder of titania (TiO₂).

Further the TiO₂ thin films were prepared in FTO substrates. The FTO substrates in 200 mm x 300 mm size and sheet resistance of 15 ohm per square were taken and washed in detergent, acetone and deionised water under ultrasonic bath. The washed substrates were dried and prepared for thin film coating. The sol-gel hydro thermally (Solvo thermal) prepared TiO₂ powder was mixed with surfactant binder Triton X100 in mortar pestle, until smooth paste formation. Then paste was applied on the FTO substrate, which was covered by scotch tape by four sides to form a slit opening of 1x1cm. The application of TiO₂ paste on the substrate was done using glass rod by doctor blade method to get even coating of TiO₂ on the FTO substrate.

For extraction of natural dyes from *Alkannatinctoria* the barks were taken and cut in to small pieces. The small pieces were soaked in 100 mL of ethanol and kept for 12 hrs in dark place. Then the residuals are filtered and washed with hexane for several times to remove oily substances in the filtrate. The pH measured was 5.1 for the dye solution. This was used directly as dye solution for sensitizing TiO₂ thin films to act as photo anodes for the solar cell.




Fig. 2: X-ray diffraction patterns of as prepared TiO₂ thin film

Crystalline and phase analysis of the films were carried out by X-ray diffraction method (RigakuRint

2000 series). The optical properties of thin film and dye were studied using the absorbance spectra of UV-Vis spectroscopy (Jasco V-570). The surface morphology of the samples was studied using scanning electron microscopy. The J-V characteristics for the solar cell are studied using Keithley 2400 and solar simulator of AM1.5. The chemical composition of TiO₂ thin films and dye were studied using Fourier Transform Infra-red spectroscopy (Bruker).

3. RESULTS AND DISCUSSION

Fig. 2 shows the XRD patterns of the as-prepared TiO₂ samples. In the XRD pattern, all the reflections correspond to the tetragonal pure phase of anatase TiO₂ (JCPDS card No. 84-1286). The shape of the diffraction peaks indicates that the product is well crystallized. No impurity phase is observed in the XRD pattern. The results clearly show that the XRD pattern has relatively sharper and narrower high-intensity reflections and this is due to the good crystallinity observed in the film. The average crystallite size was calculated from the x-ray diffraction pattern using Scherer's formula (Vetrivel *et al.* 2014). The calculated average value of grain size is 6.470 nm. The calculated lattice to tetragonal cell are $a = 3.801$ and $c = 9.502$. The obtained values are in good agreement with the standard card values and the previously reported data for anatase TiO₂ (Vetrivel *et al.* 2016).




Fig. 3: SEM image of nanocrystalline TiO₂

The morphology of the synthesized product was examined by SEM images. Fig. 3 shows the SEM image of the synthesized anatase TiO₂ particles. The image clearly shows that the synthesized samples have nanoparticles with sphere-like structure with a diameter in the range of 20-35 nm.

Fig. 4 shows the absorption region with the edge extending to 341.91 nm. The sphere-like structured nanoparticles with a rough surface morphology are responsible for reduced transmission and thereby higher

absorption. The band gap energy could be estimated using the formula $E_g = hc / \lambda$, where h and c are the Planck's constant and velocity of light, respectively, and the calculated value is 3.6 eV. However, the obtained value is at the UV part of the solar spectrum, indicating that the synthesized structures have a very good application prospect in the field of photovoltaic conversion. Therefore, photoanodes were fabricated by coating TiO₂ paste as the bottom layer and prepared dye particles as the sensitizing layer to compare the sensitizing abilities.




Fig. 4: UV-vis absorption spectra of anatase TiO₂




Fig. 5: UV-vis absorption spectra of Alkannatindoriadye

The optical properties of the prepared dye have been evaluated by means of optical absorption spectroscopy. Fig. 5 shows the broad absorption region with the edge extending to 771 nm. The band gap energy could be estimated using the formula $E_g = hc / \lambda$, where h and c are the Planck's constant and velocity of light, respectively, and the calculated value is 1.61 eV. However, the obtained value is at the red part of the solar spectrum, indicating that the dye structures have a very good application prospect in the field of photovoltaic conversion (Senthil *et al.* 2014).




Fig. 6: Comparison of UV-vis absorption spectra of *Alkanna tinctoria* dye sensitized TiO₂ thin film and as prepared TiO₂ thin film

Fig. 6 shows the absorbance spectrum of TiO₂ and TiO₂ thin film sensitized with *Alkanna tinctoria*. The broad spectrum of *Alkanna tinctoria* from 400-700 nm, which might indicate the extract contains chlorophyll mixture which shows an absorption peak in between 400-500 nm and 600-700 nm (Hernandez-Martinez *et al.* 2012) the extract also has spectrum between 476 and 545 nm and around 520 nm which could be associated with the presence of betalains (Al-Alwani *et al.* 2015) and anthocyanins (Kevin Gould and Winefield, 2009) respectively. Anthocyanin is the core component of some natural dyes and is often found in the fruits, flowers, and leaves of plants (Wongcharee *et al.* 2007). The spectrum of TiO₂ thin film sensitized with *Alkanna tinctoria* was less compared to original dye spectrum. This is due to the ratio of dye absorbance in TiO₂ thin film. The *Alkanna tinctoria* sensitized TiO₂ thin film shows broad spectrum till 500 nm and little peak in around 550 nm. This confirms betalains and anthocyanin presence in the sensitized TiO₂ thin film. The major compound present in the *Alkanna tinctoria* is Alkannin pigments, which is rich in carboxyl and hydroxyl groups. This carboxyl and hydroxyl will enable adherence of dye to TiO₂ molecules in thin film. The absorbed band gap of dye is 1.61 eV and dye sensitized TiO₂ thin film is 2.59 eV. Whereas the band gap observed for TiO₂ thin film is 3.6 eV. This shows the sensitization of dye makes the TiO₂ thin film to open up few more area in the region of visible light spectrum. After dye absorption the absorbance band of TiO₂ is broadened and red shifted.

The I-V characteristics of TiO₂ nanocrystalline thin films sensitized with *Alkannatinctoria* dye is shown in Fig. 7. The solar cell sensitized with *Alkannatinctoria*

dye extract exhibit a power conversion efficiency of 0.097 %, with a short circuit current density (J_{sc}) of 6.08E-5 A/cm², open circuit voltage (V_{oc}) of 1.62E-1 V and fill factor (FF) of 0.35. Based on investigation on the structure and properties of dye molecules, it was found that the *Alkannatinctoria* extract possesses photosensitization effect. This is due to the better interaction between the carbonyl and hydroxyl groups of anthocyanin molecule in dye extract and the TiO₂ film. Monzir Abdel-Latif *et al.* (2013) have prepared extracts from ten different plant seeds. *Alkannatinctoria* fabricated dye sensitized solar cells resulting in a power conversion efficiency of 0.02. The obtained power conversion efficiency for *Alkannatinctoria* barks extracts of 0.097 % is the best efficiency reported here for TiO₂ nanocrystalline thin film based dye sensitized solar cells.




Fig. 7: I-V graph of *Alkannatinctoria* dye sensitized TiO₂ thin film solar cell.

5. CONCLUSION

The nanocrystalline TiO₂ thin films have been prepared by sol-gel, hydrothermal and doctor blade coating method. X-ray diffraction analysis reveals that the TiO₂ nanocrystalline thin films exhibit anatase phase. The dye extracted from *Alkannatinctoria* barks strongly absorb visible light and have been found to be suitable for the use as sensitizer in solar cells. The efficiency of the fabricated dye sensitized solar cell using *Alkannatinctoria* barks extract is 0.097 %. The use of natural dyes in dye sensitized solar cells is environmentally friendly, renewable, low cost and green source of energy.

FUNDING

This research received no specific grant from any funding agency in the public, commercial, or not-for-profit sectors.

CONFLICTS OF INTEREST

The authors declare that there is no conflict of interest.

COPYRIGHT

This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC-BY) license (<http://creativecommons.org/licenses/by/4.0/>).



REFERENCES

- Al-Alwani, M. A. M., Mohamad, A. B., Kadhum, A. A. H. and Ludin, N. A., Effect of solvents on the extraction of natural pigments and adsorption onto TiO₂ for dye-sensitized solar cell applications, *Mol. Biomol. Spectrosc.*, 138, 130-137(2015).
<https://doi.org/10.1016/j.saa.2014.11.018>
- Altobello, S., Argazzi, R., Caramori, S., Contado, C., Da Fre, S., Rubino, P., Chone, C., Larramona, G. and Bignozzi, C. A., Sensitization of nanocrystalline TiO₂ with black absorbers based on Os and Rupolypyridine complexes, *J. Am. Chem. Soc.*, 127(44), 15342–15343(2005).
<https://doi.org/10.1021/ja053438d>
- Argazzi, R., Larramona, G., Contado, C. and Bignozzi, C. A., Preparation and photoelectrochemical characterization of a red sensitive osmium complex containing 4,4',4''-tricarboxy-2,2':6',2''-terpyridine and cyanide ligands, *J. Photochem. Photobiol.A*, 164(1-3), 15–21(2004).
<https://doi.org/10.1016/j.jphotochem.2003.12.016>
- Bauer, C., Boschloo, G. and Hagfeldt, A., Ultrafast studies of electron injection in Ru dye sensitized SnO₂ nanocrystalline thin film, *Int. J. Photoenergy*, 4(1), 17-20(2002).
<https://doi.org/10.1155/S1110662X0200003X>
- Calogero, G., Cazzanti, S., Caramori, S., Di Marco, G., Argazzi, R., Di Carlo, A., Bignozzi and C. A., Red Sicilian orange and purple eggplant fruits as natural sensitizers for dye-sensitized solar cells, *J. Photochem. Photobiol. A: Chemistry*, 92(11), 1341-1346(2008).
<https://doi.org/10.1016/j.solmat.2008.05.007>
- Campbell, W. M., Jolley, K. W., Wagner, P., Wagner, K., Walsh, P. J., Gordon, K. C., Schmidt-Mende, L., Nazeeruddin, M. K., Wang, Q., Graetzel, M. and Officer, D. L., Highly efficient porphyrin sensitizers for dye-sensitized solar cells, *J. Phys. Chem. C*, 111(32), 11760–11762(2007).
<https://doi.org/10.1021/jp0750598>
- Chappel, S., Chen, S. G. and Zaban, A., TiO₂-coated nanoporous SnO₂ electrodes for dye-sensitized solar cells, *Langmuir*, 18(8), 3336-3342(2002).
<https://doi.org/10.1021/la015536s>
- Cherepy, N. J., Smestad, G. P., Graetzel, M. and Zhang, G. J., Ultrafast electron injection: implications for a photoelectrochemical cell utilizing an anthocyanin dye-sensitized TiO₂ nanocrystalline electrode, *J. Phys. Chem. B*, 101(45), 9342-9351(1997).
<https://doi.org/10.1021/jp972197w>
- Dai, Q. and Rabani, J., Photosensitization of nanocrystalline TiO₂ films by pomegranate pigments with unusually high efficiency in aqueous medium, *Chem. Commun.*, 20, 2142-2143(2001).
<https://doi.org/10.1039/b106197f>
- Dai, Q. and Rabani, J., Photosensitization of nanocrystalline TiO₂ films by pomegranate pigments with unusually high efficiency in aqueous medium, *J. Photochem. Photobiol..A*, 148(1-3), 17-24(2002).
[https://doi.org/10.1016/S1010-6030\(02\)00073-4](https://doi.org/10.1016/S1010-6030(02)00073-4)
- Gerischer, H., Electrochemical techniques for the study of photosensitization, *Photochem. Photobiol.*, 16(4), 243-260(1972).
<https://doi.org/10.1111/j.1751-1097.1972.tb06296.x>
- Graetzel, M., Solar energy conversion by dye-sensitized photovoltaic cells, *Inorg.Chem.*, 44(20), 6841-6851(2005).
<https://doi.org/10.1021/ic0508371>
- Herna'ndez-Mart'inez, A. R., Estevez, M., Vargas, S., Quintanilla, F. and Rodriguez, R., Natural pigment-based dye-sensitized solar cells, *J. Appl. Res. Technol.*, 10(1), 38-47(2012).
- Kay, A. and Graetzel, M., Artificial photosynthesis. 1. Photosensitization of titania solar cells with chlorophyll derivatives and related natural porphyrins, *J. Phys. Chem.*, 97(23), 6272-6277(1993).
<https://doi.org/10.1021/j100125a029>
- Keis, K., Vayssieres, L., Lindquist, S. E. and Hagfeldt, A., Nanostructured ZnO electrodes for photovoltaic applications, *Nanostruct.Mater.*, 12(1-4), 487-490(1999).
[https://doi.org/10.1016/S0965-9773\(99\)00165-8](https://doi.org/10.1016/S0965-9773(99)00165-8)

- Kevin Gould, K. D. and Winefield, C., Anthocyanins biosynthesis, functions, and applications, Springer Science, USA(2009).
- Kuciauskas, D., Freund, M. S., Gray, H. B., Winkler, R. J. and Lewis, N. S., Photodissociation of nitric oxide from nitrosylmetalloporphyrins in micellar solutions, *J. Phys. Chem. B*, 105(2), 392-398(2001).
<https://doi.org/10.1021/jp002515i>
- Liska, P., Vlachopoulos, N., Nazeeruddin, M. K., Comte, P. and Graetzel, M., cis-Diaquabis(2,2'-bipyridyl-4,4'-dicarboxylate)ruthenium(II) sensitizes wide band gap oxide semiconductors very efficiently over a broad spectral range in the visible, *J. Am. Chem. Soc.*, 110(11), 3686–3687(1988).
<https://doi.org/10.1021/ja00219a068>
- Maldonado, S., Fitch, G. A. and Lewis, N. S., In series on photoconversion of solar energy: nanostructured and photoelectric chemical system for solar photon conversion; Archer, M. D., Nozik, A., Eds.; Imperial College Press: London, 3, 537(2007).
- Martinson, A. B. F., Goes, S. M., Fabregat-Santiago, F., Bisquert, J., Pellin, M. J. and Hupp, T. J., Electron transport in dye-sensitized solar cells based on ZnO nanotubes: evidence for highly efficient charge collection and exceptionally rapid dynamics, *J. Phys. Chem. A*, 113(16), 4015-4021(2009).
<https://doi.org/10.1021/jp810406q>
- Monzir, S., Abdel-Latif, Taher, M., El-Agez, Sofyan, A., Taya, Amal, Y., Batniji, Hatem, S. and El-Ghamri, Plant seeds-based dye-sensitized solar cells, *Mater. Sci. Appl.*, 4(9), 516-520(2013).
<https://doi.org/10.4236/msa.2013.49063>
- Nazeeruddin, M. K., Kay, A., Rodicio, I., Humphry-Baker, R., Mueller, E., Liska, P., Vlachopoulos, N. and Graetzel, M., Conversion of light to electricity by cis-X2bis (2,2'-bipyridyl-4,4'-dicarboxylate) ruthenium (II) charge-transfer sensitizers (X = Cl-, Br-, I-, CN-, and SCN-) on nanocrystalline titanium dioxide electrodes, *J. Am. Chem. Soc.*, 115(14), 6382–6390(1993).
<https://doi.org/10.1021/ja00067a063>
- Nazeeruddin, M. K., Pechy, P., Liska, P., Renouard, T., Zakeeruddin, S. M., Humphry-Baker, R., Comte, P., Cevey, L., Costa, E., Shklover, V., Spiccia, L., Deacon, G. B., Bignozzi, C. A. and Graetzel, M., Engineering of efficient panchromatic sensitizers for nanocrystalline TiO₂-based solar cells, *J. Am. Chem. Soc.*, 123(8), 1613–1624(2001).
<https://doi.org/10.1021/ja003299u>
- O'Regan, B. and Graetzel, M., A low-cost, high-efficiency solar cell based on dye-sensitized colloidal TiO₂ films, *Nat.*, 353, 737-740(1991).
<https://doi.org/10.1038/353737a0>
- Sapp, S. A., Elliott, C. M., Contado, C., Caramori, S. and Bignozzi, C. A., Substituted polypyridine complexes of cobalt(II/III) as efficient electron-transfer mediators in dye-sensitized solar cells, *J. Am. Chem. Soc.*, 124(37), 11215–11222(2002).
<https://doi.org/10.1021/ja027355y>
- Sarto Polo, A. and Murakami Iha, N. Y., Blue sensitizers for solar cells: Natural dyes from Calafate and Jaboticaba, *Sol. Energy Mater. Sol. Cells*, 90(13), 1936-1944(2006).
<https://doi.org/10.1016/j.solmat.2006.02.006>
- Sayama, K., Sugihara, H. and Arakawa, H., Photoelectrochemical properties of a porous Nb₂O₅ electrode sensitized by a ruthenium dye, *Chem. Mater.*, 10(12), 3825-3832(1998).
<https://doi.org/10.1021/cm980111i>
- Senthil, T. S., Muthukumarasamy, N. and Misook Kang, Ball/dumbbell-like structured micrometer-sized Sb₂S₃ particles as a scattering layer in dye-sensitized solar cells, *Opt. Lett.*, 39(7), 1865-1868(2014).
<https://doi.org/10.1364/OL.39.001865>
- Tennakone, K., Kumara, G. R., Kottegoda, I. R. and Wijayantha, K., The photostability of dye-sensitized solid state photovoltaic cells: factors determining the stability of the pigment in a nanoporous n/cyanidin/p-CuI cell, *Semicond. Sci. Technol.*, 12(1), 128-132(1997).
<https://doi.org/10.1088/0268-1242/12/1/021>
- Tian, H., Yang, X. and Hagfeldt, A., A metal-free “black dye” for panchromatic dye-sensitized solar cells, *Energy Environ. Sci.*, 2, 674-677(2009).
<https://doi.org/10.1039/b901238a>
- Tributsch, H. and Calvin, M., Electrochemistry of excited molecules: photoelectrochemical reaction of chlorophylls, *Photochem. Photobiol.*, 14(2), 95-112(1971).
<https://doi.org/10.1111/j.1751-1097.1971.tb06156.x>
- Vetrivel, V., Rajendran, K., Senthil, T. S., Anbarasu, P., Structural and optical characteristics transformation in the sol-gel synthesized pure titanium dioxide, *J. Environ. Nanotechnol.*, 5(1), 8-12(2016).
<https://doi.org/10.13074/jent.2016.03.161179>

- Vetrivel, V., Rajendran, K. and Kalaiselvi, V., Synthesis and characterization of pure titanium dioxide nanoparticles by sol-gel method, *Int. J. Chem. Tech. Res.*, 7(3), 1090-1097(2014).
- Wongcharee, K., Meeyoo, V. and Chavadej, S., Dye-sensitized solar cell using natural dyes extracted from rosella and blue pea flowers, *Sol. Energy Mater. Sol. Cells*, 91(7), 566-571 (2007).
<https://doi.org/10.1016/j.solmat.2006.11.005>
- Yum, J. H., Walter, P., Huber, S., Rentsch, D., Geiger, T., Neusch, F., DeAngelis, F., Graetzel, M. and Nazeeruddin, M. K., Efficient far red sensitization of nanocrystalline TiO₂ films by an unsymmetrical squaraine dye, *J. Am. Chem. Soc.*, 129(34), 10320–10321(2007).
<https://doi.org/10.1021/ja0731470>
- Zhang, D., Lanier, S. M., Downing, J. A., Avent, J. L., Lum, J. and McHale, J. L., Betalain pigments for dye-sensitized solar cells, *J. Photochem. Photobiol. A*, 195(1), 72–80(2008).
<https://doi.org/10.1016/j.jphotochem.2007.07.038>